

# Aluminium Alloy 4015

Aluminium alloy 4015 is a high quality general purpose alloy featuring good ductility coupled with mechanical strength. A close relation to 3103 AlMn alloy, but with higher Silicon content, **this alloy can be welded, anodized\* or painted.** It should be noted that the anodized finish of alloy 4015 will be much darker and less reflective than on alloys 1050 or 3103 so this is not recommended for decorative applications. Many users now prefer to use alloy 4015 having switched from other alloys such as 1050 and 3103.

The **corrosion resistance** of alloy 4015 is similar to the 3000 series alloys. Suitable for most applications in mill finish or painted, it is not recommended for use in aggressive environments.

*\* It should be noted that the anodized finish on alloy 4015 will be much darker and less reflective than on alloys 1050 or 3103 so this is not recommended for decorative applications.*

## Chemical Composition

Si	1.4 to 2.2%
Fe	0.7%
Cu	0.2%
Mn	0.6 to 1.2%
Mg	0.10 to 0.50%
Zn	0.2%

## Mechanical Properties

Temper	Rp0.2% MPa	UTS MPa	A Min %
0	45 Min	110-150	20
H12	110 Min	135-175	4
H14	135 Min	160-200	3
H16	155 Min	185-225	2
H18	180 Min	210-250	2

## Physical Properties

Density	2.72 g mm <sup>-3</sup>
Melting Point	600°C
Modulus of Elasticity	Approx 70 GPa
Electrical Resistivity	23-29x10 <sup>8</sup> Ωm
Thermal Conductivity	150-200 W/mK
Thermal Expansion	24x10 <sup>-6</sup> /K

## Formability

Equivalent to alloy 3103 in same temper. r/t performance dependent upon thickness – Approx figures for H12 are shown below

Thickness mm	r/t min bend radius for 180° bend
0.5-0.8	0.0
0.8-1.5	1.0
1.5-3.0	2.0

## Drawability

Typical properties for 0.8mm thick sheet

Temper	r/t	r value <sup>1</sup>	Erichsen Value <sup>2</sup> (mm)
0	45 Min	110-150	20
H12	110 Min	135-175	4
H14	135 Min	160-200	3
H16	155 Min	185-225	2
H18	180 Min	210-250	2

<sup>1</sup> An indication of drawability

<sup>2</sup> An indication of limit of biaxial stretching

## Welding

Suitable for MIG and TIG welding using normal aluminium welding conditions. Recommended welding wire is 4043 (Al Si5)

Typical welding conditions are shown below

Parameter	MIG	TIG
Current	120A	150A
Voltage	20V	14V
Travel Speed	0.65m/min	0.22m/min
Wire Feed rate	5.2m/min	-
Gas Flow Rate	25l/min	9l/min

*This information is based on our present knowledge and is given in good faith. However, no liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon*

*As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose. Any advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company.*

*Any contract between the Company and a customer will be subject to the Company's Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.*

**aalco**<sup>®</sup>

Aalco is a registered trademark of Aalco Metals Ltd

© Copyright: Aalco Metals Ltd, 25 High Street, Cobham, Surrey, KT11 3DH

*All Data is indicative only and must not be seen as a substitute for the full specification from which it is drawn. In particular, the mechanical property requirements vary widely with temper, product form and product dimensions. For more complete details please refer to the relevant specification – The BS EN Specifications for aluminium are listed on a separate Datasheet.*