

The old BS1474 - 1987 standard has been replaced by a number of EN standards of which the most important are:

- EN754 - Cold drawn rod, bar & tube
- EN755 - Hot extruded products
- EN12020 - Extruded precision profiles in alloys 6060 & 6063
- EN515 - Temper Designations
- EN573-1: Numerical alloy designation system
- EN573-2: Chemical symbol designation system
- EN573-3: Chemical Compositions
- EN573-4: Product forms in different alloys

For those familiar with the old BS1474 it is useful to highlight where the new EN standards differ:

- Chemical Compositions – No Change.
- Alloy Numbering System – No Change.
- Temper Designations for Heat Treatable Alloys – A new wider range of special tempers having up to four digits after the T have been introduced for non-standard applications (e.g. T6151).
- Temper Designations for Non Heat Treatable Alloys – No change to existing tempers but a more comprehensive definition of how tempers are achieved. Soft (O) temper is now classified H111 and an intermediate temper H112 is introduced. For alloy 5251 tempers are now shown as H32/H34/H36/H38 (equivalent to H22/H24, etc). H19/H22 & H24 are now shown separately.

Chemical Compositions

Please refer to the datasheet entitled Aluminium Specifications.

Mechanical Properties

Please refer to the datasheet entitled Aluminium Specifications.

Note that for the purposes of tolerances the alloys are split into two groups:

- Group I – 1000 series, 3000 series, 6000 series, 5005, 5051, 5251
- Group II – 2000 series, 7000 series, 5052, 5154, 5454, 5754, 5083, 5086

ALLOY GROUPS

Alloy Group I
1050, 1070, 1200, 1350, 3102, 3003, 3103
5005, 5005A, 5051A, 5251
6101A, 6101B, 6005, 6005A, 6106, 6008, 6010A, 6012, 6014, 6018, 6023, 6351, 6060, 6360,
6061, 6261, 6262, 6262A, 6063, 6063A, 6463, 6065, 6081, 6082, 6182
Alloy Group II
2007, 2011, 2011A, 2014, 2014A, 2017A, 2024, 2030
5019, 5049, 5052, 5154A, 5454, 5754, 5083, 5086
7003, 7005, 7108, 7108A, 7020, 7021, 7022, 7049A, 7075

DIAMETER TOLERANCES - ROUND BAR

Diameter mm	Tolerances mm (+/-)	Tolerances mm (+/-)
	Group I	Group II
8 to 18	0.22	0.30
19 to 25	0.25	0.35
26 to 40	0.30	0.40
41 to 50	0.35	0.45
51 to 65	0.40	0.50
66 to 80	0.45	0.70
81 to 100	0.55	0.90
101 to 120	0.65	1.0
121 to 150	0.80	1.2
151 to 180	1.0	1.4
181 to 220	1.15	1.7
221 to 270	1.3	2.0
271 to 320	1.6	2.5

DIMENSIONAL TOLERANCES - SQUARE BAR

Width Across Flats (mm)	Tolerances mm (+/-)	Tolerances mm (+/-)
	Group I	Group II
10 to 18	0.22	0.30
19 to 25	0.25	0.35
26 to 40	0.30	0.40
41 to 50	0.35	0.45
51 to 65	0.40	0.50
66 to 80	0.45	0.70
81 to 100	0.55	0.90
101 to 120	0.65	1.0
121 to 150	0.80	1.2
151 to 180	1.0	1.4
181 to 220	1.15	1.7

DIMENSIONAL TOLERANCES - HEXAGON BAR

Width Across Flats (mm)	Tolerances mm (+/-)	Tolerances mm (+/-)
	Group I	Group II
10 to 18	0.22	0.30
19 to 25	0.25	0.35
26 to 40	0.30	0.40
41 to 50	0.35	0.45
51 to 65	0.40	0.50
66 to 80	0.50	0.70
81 to 100	0.55	0.90
101 to 120	0.65	1.0
121 to 150	0.80	1.2
151 to 180	1.0	1.4
181 to 220	1.15	1.7

WIDTH TOLERANCE - RECTANGULAR BARS

Width Across Flats (mm)	Tolerances mm (+/-)	Tolerances mm (+/-)
	Group I	Group II
10 to 18	0.25	0.35
19 to 30	0.30	0.40
31 to 50	0.40	0.50
51 to 80	0.60	0.70
81 to 120	0.80	1.0
121 to 180	1.0	1.4
181 to 240	1.4	1.8
241 to 350	1.8	2.2
351 to 450	2.2	2.8
451 to 600	3.0	3.5

SQUARENESS TOLERANCES - RECTANGULAR BAR

Width Across Flats (mm)	Max Deviation from Square (mm)
2 to 10	0.1
11 to 100	0.01 x Width Across Flats
101 to 180	1.0
181 to 240	1.5

SQUARENESS TOLERANCES - SQUARE BARS

Width Across Flats (mm)	Max Deviation from Square (mm)
10 to 100	0.01 x Width across Flats
101 to 180	1.0
181 to 220	1.5

MAX CORNER RADII - SQUARE BARS

Width Across Flats (mm)	Tolerances mm (+/-)	Tolerances mm (+/-)
	Group I	Group II
10 to 25	1.0	1.5
26 to 50	1.5	2.0
51 to 80	2.0	3.0
81 to 120	2.5	3.0
121 to 180	2.5	4.0
181 to 220	3.5	5.0

THICKNESS TOLERANCES FOR RECTANGULAR
BAR - GROUP I

Width Across Flats (mm)	Tols +/-	Tols +/-	Tols +/-	Tols +/-	Tols +/-
	2-6mm	6.1 - 10mm	10.1- 18mm	19- 30mm	31- 50mm
10 to 18	0.20	0.25	0.25	-	-
19 to 30	0.20	0.25	0.30	0.3	-
31 to 50	0.25	0.25	0.30	0.35	0.4
51 to 80	0.25	0.30	0.35	0.40	0.5
81 to 120	0.30	0.35	0.40	0.45	0.6
121 to 180	0.40	0.45	0.50	0.55	0.6
181 to 240	-	0.55	0.60	0.65	0.7
241 to 350	-	0.65	0.70	0.75	0.8
351 to 450	-	-	0.80	0.85	0.9
451 to 600	-	-	-	-	0.9

THICKNESS TOLERANCES FOR RECTANGULAR
BAR - GROUP I

Width Across Flats (mm)	Tols +/-	Tols +/-	Tols +/-	Tols +/-
	51-80mm	81- 120mm	121- 180mm	181- 240mm
10 to 18	-	-	-	-
19 to 30	-	-	-	-
31 to 50	-	-	-	-
51 to 80	0.6	-	-	-
81 to 120	0.7	0.8	-	-
121 to 180	0.7	0.9	1.0	-
181 to 240	0.8	1.0	1.2	1.4
241 to 350	0.9	1.1	1.3	1.5
351 to 450	1.0	1.2	1.4	1.6
451 to 600	1.0	1.4	-	-

THICKNESS TOLERANCES FOR RECTANGULAR
BAR-GROUP II

Width Across Flats (mm)	Tols +/-	Tols +/-	Tols +/-	Tols +/-	Tols +/-
	2-6mm	6.1- 10mm	10.1- 18mm	19- 30mm	31- 50mm
10 to 18	0.25	0.30	0.35	-	-
19 to 30	0.25	0.30	0.40	0.40	-
31 to 50	0.30	0.30	0.40	0.5	0.5
51 to 80	0.30	0.35	0.45	0.6	0.7
81 to 120	0.35	0.40	0.5	0.6	0.7
121 to 180	0.45	0.50	0.55	0.7	0.8
181 to 240	-	0.60	0.65	0.7	0.9
241 to 350	-	0.70	0.75	0.8	0.9
351 to 450	-	-	0.9	1.0	1.1
451 to 600	-	-	-	-	1.2

THICKNESS TOLERANCES FOR RECTANGULAR
BAR-GROUP II

Width Across Flats (mm)	Tols +/-	Tols +/-	Tols +/-	Tols +/-
	51-80mm	81- 120mm	121- 180mm	181- 240mm
10 to 18	-	-	-	-
19 to 30	-	-	-	-
31 to 50	-	-	-	-
51 to 80	0.7	-	-	-
81 to 120	0.8	1.0	-	-
121 to 180	1.0	1.1	1.4	-
181 to 240	1.1	1.3	1.6	1.8
241 to 350	1.2	1.4	1.7	1.9
351 to 450	1.4	1.8	2.1	2.3
451 to 600	1.4	1.8	-	-

DIAMETER TOLERANCES FOR SMLS & PORTHOLE
ROUND TUBE

Diam. (mm) OD or ID	Max Deviation of Mean Diam.	Max Dev. at Any Point mm	Max Dev. at Any Point mm	Max Dev. at Any Point mm
	mm (+/-)	Not Annealed or Heat Treated	Heat- Treated	Annealed
8 to 18	0.25	0.4	0.6	1.5
19 to 30	0.30	0.5	0.7	1.8
31 to 50	0.35	0.6	0.9	2.2
51 to 80	0.40	0.7	1.1	2.6
81 to 120	0.60	0.9	1.4	3.6
121 to 200	0.90	1.4	2.0	5.0
201 to 350	1.4	1.9	3.0	7.6
351 to 450	1.9	2.8	4.0	10.0

WALL THICKNESS TOLS FOR SEAMLESS ROUND
TUBE

Wall Thickness (mm)	Tolerance Measured at any Point (+/- %)
0.5 to 3.0	10
3.0 to 5.0	9
Over 5.0	8

TOL - WIDTH,DEPTH,WIDTH A/F FOR SMLS &
P/HOLE TUBE

Width, Depth or Width A/F	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)
	Group I 0 to 100mm	Group I 101 to 200	Group I 201 to 300	Group I 301 to 350
Up to 10	0.25	0.30	0.35	0.40
11 to 25	0.30	0.40	0.50	0.60
26 to 50	0.50	0.60	0.80	0.90
51 to 100	0.70	0.90	1.10	1.30
101 to 150	-	1.10	1.30	1.50
151 to 200	-	1.30	1.50	1.80
201 to 300	-	-	1.70	2.10
301 to 350	-	-	-	2.80

TOL - WIDTH,DEPTH,WIDTH A/F FOR SMLS &
P/HOLE TUBE

Width, Depth or Width A/F	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)	Ovality Tols (+/- mm)
	Group II 0 to 100mm	Group II 101 to 200mm	Group II 201 to 300mm	Group II 301 to 350mm
Up to 10	0.40	0.50	0.55	0.60
11 to 25	0.50	0.70	0.80	0.90
26 to 50	0.80	0.90	1.0	1.20
51 to 100	1.0	1.20	1.30	1.60
101 to 150	-	1.50	1.70	1.80
151 to 200	-	1.90	2.20	2.40
201 to 300	-	-	2.50	2.80
301 to 350	-	-	-	3.50

TOLS ON WT FOR SMLS TUBE - OTHER THAN
ROUND TUBE

Wall Thickness (mm)	Tols (+/- mm) for given Circumscrib- ing Circle	Tols (+/- mm) for given Circumscrib- ing Circle	Tols (+/- mm) for given Circumscrib- ing Circle
	Up to 100mm Group I	101 to 300mm Group I	301 to 350mm Group I
0.5 to 1.5	0.25	0.35	-
1.51 to 3.0	0.30	0.50	0.75
3.1 to 6.0	0.50	0.75	1.0
6.1 to 10	0.75	1.0	1.2
11 to 15	1.0	1.2	1.5
16 to 20	1.5	1.9	2.0
31 to 30	1.9	2.2	2.5
31 to 40	-	2.5	2.7

TOLS ON WT FOR SMLS TUBE - OTHER THAN ROUND TUBE

Wall Thickness (mm)	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle
	Up to 100mm Group II	101 to 300mm Group II	301 to 350mm Group II
0.5 to 1.5	0.35	0.50	-
1.51 to 3.0	0.45	0.65	0.9
3.1 to 6.0	0.60	0.90	1.2
6.1 to 10	1.0	1.3	1.5
11 to 15	1.3	1.7	1.9
16 to 20	1.9	2.2	2.5
21 to 30	2.2	2.7	3.1
31 to 40	-	-	-

TOLS ON WT FOR P/HOLE TUBE - OTHER THAN ROUND TUBE

Wall Thickness (mm)	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle
	Up to 100mm Group I	101 to 300mm Group I	301 to 350mm Group I
0.5 to 1.5	0.20	0.30	-
1.51 to 3.0	0.25	0.40	0.60
3.1 to 6.0	0.40	0.60	0.80
6.1 to 10.0	0.60	0.80	1.0
11 to 15	0.80	1.0	1.2
16 to 20	1.2	1.5	1.7
21 to 30	1.5	1.8	2.0
31 to 40	-	2.0	2.0

WALL THICKNESS TOLERANCES FOR PORTHOLE ROUND TUBE

Wall Thickness (mm)	Tolerance Measured at Any Point (+/- %)
3.0	7
3.0 to 5.0	6
Over 5.0	5

TOLS ON WT FOR P/HOLE TUBE - OTHER THAN ROUND TUBE

Wall Thickness (mm)	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle	Tols (+/- mm) for given Circumscribing Circle
	Up to 100mm Group II	101 to 300mm Group II	301 to 350mm Group II
0.5 to 1.5	0.30	0.40	-
1.51 to 3.0	0.35	0.50	0.70
3.1 to 6.0	0.55	0.70	0.90
6.1 to 10	0.75	1.0	1.2
11 to 15	1.0	1.3	1.5
16 to 20	1.5	1.8	2.0
21 to 30	1.8	2.2	2.5
31 to 40	-	2.5	3.0

CONTACT

Address:	Please make contact directly with your local service centre, which can be found via the Locations page of our web site
Web:	www.aalco.co.uk

REVISION HISTORY

Datasheet Updated	18 July 2019
--------------------------	--------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.