

SPECIFICATIONS

Commercial	410
EN	1.4006

Grade 410 / 1.4006 is a hardenable martensitic stainless steel available in bar form only.

CHEMICAL COMPOSITION

EN 10088-3:2005 1.4006 Steel	
Element	% Present
Chromium (Cr)	11.50 - 13.50
Manganese (Mn)	0.0 - 1.50
Silicon (Si)	0.0 - 1.00
Nickel (Ni)	0.0 - 0.75
Carbon (C)	0.08 - 0.15
Phosphorous (P)	0.0 - 0.04
Sulphur (S)	0.0 - 0.02
Iron (Fe)	Balance

ALLOY DESIGNATIONS

1.4006 is similar, **but may not be a direct equivalent to:**

410S
UNS S41000
410S21

SUPPLIED FORMS

- Bar

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	7.75 g/cm ³
Thermal Expansion	9.9 x10 ⁻⁶ /K
Modulus of Elasticity	300 GPa
Thermal Conductivity	24.9 W/m.K
Electrical Resistivity	0.57 x10 ⁻⁶ Ω .m

MECHANICAL PROPERTIES

EN 10088-3:2005 Bar Up to 160mm Dia or Thickness	
Property	Value
Proof Stress	450 Min MPa
Tensile Strength	650 - 850 MPa
Elongation A	15 Min %

Mechanical properties vary significantly according to heat treatment temperature.

Material in the annealed condition shall have a hardness reading of 220 HB Max and a Tensile Test reading Of 730 MPA Max.

CORROSION RESISTANCE

Moderate in non-chloride containing environments

CONTACT

Address: Please make contact directly with your local service centre, which can be found via the Locations page of our web site
Web: www.aalco.co.uk

REVISION HISTORY

Datasheet Updated 13 March 2020

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.