

Stainless Steel: 1.4404 (316L) & Sheet and Plate (Quarto Plate CPP)



SPECIFICATIONS

Commercial 316L

Quarto Plate is hot rolled plate over 12mm thick that has not been coiled during production.

CPP is Continuously Produced Plate up to 12mm thick that has been coiled during rolling.

Sheet is Cold Rolled.

Stainless steel types 1.4401 and 1.4404 are also known as grades 316 and 316L respectively. Grade 316 is an austenitic grade second only to 304 in commercial importance.

316 stainless steel contains an addition of molybdenum that gives it improved corrosion resistance. This is particularly apparent for pitting and crevice corrosion in chloride environments.

316L, the low carbon version of 316 stainless steel, is immune to grain boundary carbide precipitation (sensitisation). This makes it suited to use in heavy gauge (over about 6mm) welded components.

For elevated temperature applications the high carbon variant, 316H stainless steel and the stabilised grade 316Ti stainless steel should be employed.

The austenitic structure of 316 stainless steel gives excellent toughness, even at cryogenic temperatures. Property data given in this document is typical for flat rolled products covered by EN 10088-2:2005. ASTM, EN or other standards may cover all products sold. It is reasonable to expect specifications in these standards to be similar but not necessarily identical to those given in this datasheet.

Stainless steel grade 316Ti contains a small amount of titanium. Titanium content is typically only around 0.5%. The titanium atoms stabilise the structure of the 316 at temperatures over 800°C. This prevents carbide precipitation at the grain boundaries and protects the metal from corrosion. The main advantage of 316Ti is that it can be held at higher temperatures for a longer period without sensitisation (precipitation) occurring. 316Ti retains physical and mechanical properties similar to standard grades of 316.

CHEMICAL COMPOSITION

EN 10088-2:2005
1.4404 Steel

| Element | % Present |
|-----------------|---------------|
| Chromium (Cr) | 16.50 - 18.50 |
| Nickel (Ni) | 10.00 - 13.00 |
| Molybdenum (Mo) | 2.00 - 2.50 |
| Manganese (Mn) | 0.0 - 2.00 |
| Silicon (Si) | 0.0 - 1.00 |
| Nitrogen (N) | 0.0 - 0.11 |
| Phosphorous (P) | 0.0 - 0.05 |
| Carbon (C) | 0.0 - 0.03 |
| Sulphur (S) | 0.0 - 0.02 |
| Iron (Fe) | Balance |

ALLOY DESIGNATIONS

Stainless Steel Grade 1.4404/316L also corresponds to the following designations **but may not be a direct equivalent:**

UNS S31603
316S11

SUPPLIED FORMS

- Sheet
- Strip
- Tube
- Bar
- Pipe
- Plate
- Fittings & Flanges

GENERIC PHYSICAL PROPERTIES

| Property | Value |
|------------------------|-----------------------------|
| Density | 8.0 g/cm ³ |
| Melting Point | 1400 °C |
| Thermal Expansion | 15.9 x10 ⁻⁶ /K |
| Modulus of Elasticity | 193 GPa |
| Thermal Conductivity | 16.3 W/m.K |
| Electrical Resistivity | 0.74 x10 ⁻⁶ Ω .m |

MECHANICAL PROPERTIES

EN 10088-2:2005
Sheet
Up to 8mm Thick

| Property | Value |
|-------------------|----------------|
| Proof Stress | 240 Min MPa |
| Tensile Strength | 530 to 680 MPa |
| Elongation A50 mm | 40 Min % |

Properties above are for 1.4404 sheet / plate

EN 10088-2:2005
Plate
From 8mm to 75mm Thick

| Property | Value |
|-------------------|----------------|
| Proof Stress | 220 Min MPa |
| Tensile Strength | 520 to 670 MPa |
| Elongation A50 mm | 45 Min % |

Properties above are for 1.4404 sheet / plate

APPLICATIONS

Initially developed for use in paper mills 316 stainless steel is now typically used in:

- Food processing equipment
- Brewery equipment
- Chemical and petrochemical equipment
- Laboratory benches & equipment
- Coastal architectural panelling
- Coastal balustrading
- Boat fittings
- Chemical transportation containers
- Heat exchangers
- Mining screens
- Nuts and bolts
- Springs
- Medical implants

CORROSION RESISTANCE

Grade 316 has excellent corrosion resistance when exposed to a range of corrosive environments and media. It is usually regarded as "marine grade" stainless steel but is not resistant to warm sea water. Warm chloride environments can cause pitting and crevice corrosion. Grade 316 is also subject to stress corrosion cracking above around 60°C.

HEAT RESISTANCE

316 has good resistance to oxidation in intermittent service to 870°C and in continuous service to 925°C. However, continuous use at 425-860°C is not recommended if corrosion resistance in water is required. In this instance 316L is recommended due to its resistance to carbide precipitation. Where high strength is required at temperatures above 500°C, grade 316H is recommended.

FABRICATION

Fabrication of all stainless steels should be done only with tools dedicated to stainless steel materials. Tooling and work surfaces must be thoroughly cleaned before use. These precautions are necessary to avoid cross contamination of stainless steel by easily corroded metals that may discolour the surface of the fabricated product.

COLD WORKING

Grade 316 is readily brake or roll formed into a variety of parts. It is also suited to stamping, heading and drawing but post work annealing is recommended to relieve internal stresses. Cold working will increase both strength and hardness of 316 stainless steel.

HOT WORKING

All common hot working processes can be performed on 316 stainless steel. Hot working should be avoided below 927°C. The ideal temperature range for hot working is 1149-1260°C. Post-work annealing is recommended to ensure optimum corrosion resistance.

MACHINABILITY

316 stainless steel has good machinability. Machining can be enhanced using the following rules:

- ~ Cutting edges must be kept sharp. Dull edges cause excess work hardening.
- ~ Cuts should be light but deep enough to prevent work hardening by riding on the surface of the material.
- ~ Chip breakers should be employed to assist in ensuring swarf remains clear of the work
- ~ Low thermal conductivity of austenitic alloys results in heat concentrating at the cutting edges. This means coolants and lubricants are necessary and must be used in large quantities.

HEAT TREATMENT

316 stainless steel cannot be hardened by heat treatment.

Solution treatment or annealing can be done by rapid cooling after heating to 1010-1120°C.

WELDABILITY

Fusion welding performance for 316 stainless steel is excellent both with and without fillers. Recommended filler rods and electrodes for 316 and 316L are the same as the base metal, 316 and 316L respectively. Heavy welded sections may require post-weld annealing. Grade 316Ti may be used as an alternative to 316 in heavy section welds.

Oxyacetylene welding has not been found to be successful for joining of 316 stainless steel.

CONTACT

Address: Please make contact directly with your local service centre, which can be found via the Locations page of our web site
Web: www.aalco.co.uk

REVISION HISTORY

Datasheet Updated 13 March 2020

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.